

- Durable foam logs allow vehicles to drive over them and still retain their original shape
- Foam logs are covered with a fuel resistant Polyethylene
- Easily drains through 3/4" drains
- Heavy-duty 30 oz fabric is compatible for water, all hydrocarbons and most chemicals
- Meets US regulations for spill containment
- Easy cleaning and storage allows for repeated Use
- Includes a patch kit and 20 extra zip ties
- Available in a variety of colors including Black, OD Green, Desert Tan and Blue
- Custom sizes are available upon request



Part #	Dimensions	Gallons
FB554	5' x 5' x 4"	62 gal
FB884	8' x 8' x 4"	160 gal
FB10104	10' x 10' x 4"	249 gal
FB12364	12' x 36' x 4"	1,077 gal
FB14545	14' x 54' x 4"	1,885 gal

*This data is provided for informational purposes only. GeoCHEM, Inc. makes no warranties as to the suitability or the fitness for a specific use or merchantability of products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check GeoCHEM, Inc. for current updates.*

# SPEC SHEET – Foam Berm

## Gallons and dims by wall size

Width	Length	2"/ Gallons	2"/Outside Dims	4"/ Gallons	4"/Outside Dims
10'	10'	150	10'-4" X 10'-4"	246	10'-8" X 10'-8"
10'	20'	239	10'-4" X 20'-4"	493	10'-8" X 20'-8"
12'	36'	517	12'-4" X 36'-4"	1066	14'-8" X 36'-8"
14'	54'	904	14'-4" X 54'-4"	1866	14'-8" X 54'-8"

Fabric: 30 oz. Hydrocarbon / chemical resistant

Standard Colors: Black, Tan, Green

Base Fabric Type	US	Metric
	Polyester	
Base Fabric Weight (nominal)	8 oz/yd <sup>2</sup>	270 g/m <sup>2</sup>
Thickness	36 mils min	0.91 mm
Weight	30.0+ <sub>-</sub> 2 oz/yd <sup>2</sup>	1020+ <sub>-</sub> 70 g/m <sup>2</sup>
Tear Strength, Tongue D751B	120/120 lb min	534/534 N min
Breaking Yield Strength ASTM D 751, Grab Tensile, Procedure	625/600 lb min	2780/2670 N min
Low Temperature ASTM D 2136,	Pass @ -40 F	Pass @ -40 C
Dimensional Stability ASTM D 1204, 212 F- 1 hr	2.5% max each direction	
Adhesion - Heat Sealed Seam ASTM D 751, Dielectric Weld	25 lb/2 in min	111 N/5 cm min
Bursting Strength ASTM D 751, Ball Tip	1000 lb min	4450 N
Hydrostatic Resistance ASTM D 751, Method A	800 psi min	540 N/sq cm min
Blocking Resistance ASTM D 751, 180 F/82 C	# 2 Rating max	
UV Resistance	8000 hrs	
Puncture Resistance ASTM D 4833	220 lb min	1110 N min

*This data is provided for informational purposes only. GeoCHEM, Inc. makes no warranties as to the suitability or the fitness for a specific use or merchantability of products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check GeoCHEM, Inc. for current updates.*