

SG 700

Uni-Axial Knitted Geogrid

STRATAGRID is geogrid reinforcement for soil. These high performance geogrids are constructed of high molecular weight and high tenacity polyester yarns utilizing a complex knitting process and polymer coating to provide superior engineering properties. Yarns are precision knitted into a dimensionally stable, uniform network of apertures providing significant tensile reinforcement capacity. STRATAGRID is engineered to be mechanically and chemically durable, in both the harsh construction installation phase and in aggressive soil environments (pH range from 3-9).

PROPERTY	TEST METHOD	ENGLISH	METRIC
Ultimate Strength	ASTM D-6637 Method A	11,800 lbs/ft	172.2 kN/m
Creep Limited Strength	ASTM D-5262/D-6992	7,613 lbs/ft	111.1 kN/m
LTDS (SW, SP, SM, SC)	LTDS or Tal	6,292 lbs/ft	91.8 kN/m
LTDS (GP, GW, GM, GC, SW, SP, SM, SC)	LTDS or Tal	6,018 lbs/ft	87.8 kN/m
LTDS (GW, GP, GM, GC)	LTDS or Tal	5,127 lbs/ft	74.8 kN/m
Molecular Weight (min.)	GRI GG8	-	25,000 g/mol
Carboxyl End Group Count (max.)	GRI GG7	-	30 Meg/kg
Aperture Size	Measured	2.45 x 0.95 in	62.2 x 24.1 mm

ROLL SIZE	AREA	WEIGHT
6' x 300'	200 sys	170 lbs
12' x 225'	300 sys	330 lbs

REDUCTION FACTOR	VALUE
RF(id) Soil - 20mm minus, D50 ≤ 0.2mm (SW, SP, SM, SC)	1.10
RF(id) Soil - 25mm minus, D50 ≤ 8mm (GP, GW, GM, GC, SW, SP, SM, SC)	1.15
RF(id) Soil - 50mm minus, D50 ≤ 20mm (GW, GP, GM, GC)	1.35
RF(d) (3 ≤ pH ≤ 9) (PET - CEG < 30, MW > 25,000)	1.10

SOIL INTERACTION COEFFICIENT	VALUE
Silts/Clay (ML, CL)	0.6 - 0.7
Sandy Silts & Clay (SC,GC)	0.7 - 0.8
Poorly-Graded Sand & Gravel, Silty Sand (GP, GM, SP, SM)	0.8 - 0.9
Well-Graded Gravel, Sand Gravel Mix, Well-Graded Sand (SW, GW)	0.9 - 1.0

This information is provided for reference only and is not intended as a warranty or guarantee. GeoCHEM, Inc. assumes no liability in connection with the use of this information (1/2013).

GeoCHEM, Inc. - Phone: (907) 562.5755 ~ Fax: 206.219.3740
 WA State Sales - Phone: (206) 774.8777 ~ Toll Free: 1 (800) 490.5320
<http://www.geocheminc.com>

