



GeoCHEM
INCORPORATED

FLEXWALL BERM

- Takes only minutes to set-up; fast and easy deployment
- Innovative design allows driver to enter/exit without leaving the vehicle
- Heavy-duty 30 oz fabric is compatible for water, all hydrocarbons and most chemicals
- In the event of a spill, walls automatically rise
- Meets EPA regulations for spill containment
- Compact design takes very little space to store
- Easy cleaning and storage allows for repeated use
- All Flexwall Berms have patch kit included
- Available in a variety of colors including Black, OD Green, Desert Tan and Blue
- Custom sizes are available upon request



Part #	Dimensions	Gallons
FW5512	5' X 5' X 12"	187 gal
FW8812	8' X 8' X 12"	473 gal
FW101012	10' X 10' X 12"	748 gal
FW123612	12' X 36' X 12"	3,231 gal
FW145412	14' X 54' X 12"	5,650 gal

SPEC SHEET – Flexwall Berm

Fabric: 30 oz. Hydrocarbon / chemical resistant

Standard Colors: Black, Tan, Green

US

Metric

Base Fabric Type	Polyester	
	US	Metric
Base Fabric Weight (nominal)	8 oz/yd ²	270 g/m ²
Thickness	36 mils min	0.91 mm
Weight	30.0+ ₋ 2 oz/yd ²	1020+ ₋ 70 g/m ²
Tear Strength, Tongue D751B	120/120 lb min	534/534 N min
Breaking Yield Strength ASTM D 751, Grab Tensile, Procedure	625/600 lb min	2780/2670 N min
Low Temperature ASTM D 2136,	Pass @ -40 F	Pass @ -40 C
Dimensional Stability ASTM D 1204, 212 F- 1 hr	2.5% max each direction	
Adhesion - Heat Sealed Seam ASTM D 751, Dielectric Weld	25 lb/2 in min	111 N/5 cm min
Bursting Strength ASTM D 751, Ball Tip	1000 lb min	4450 N
Hydrostatic Resistance ASTM D 751, Method A	800 psi min	540 N/sq cm min
Blocking Resistance ASTM D 751, 180 F/82 C	# 2 Rating max	
UV Resistance	8000 hrs	
Puncture Resistance ASTM D 4833	220 lb min	1110 N min

This data is provided for informational purposes only. GeoCHEM, Inc. makes no warranties as to the suitability or the fitness for a specific use or merchantability of products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check GeoCHEM, Inc. for current updates.

Sales & Procurement Center - Phone No. (907) 562-5755 ~ Fax No. 206.219.3740
 WA State Sales - Phone No. (206) 774.8777 ~ Toll Free: 1 (800) 490.5320
 GeoCHEM Website: <http://www.geocheminc.com>
 Contact Us: <http://www.geocheminc.com/contactus.php>