



# SNAP UP BERM

- Snap-up support provides a sturdy side wall for excellent spill containment
- 100% usable interior space
- Heavy-duty 30 oz fabric is compatible for water, all hydrocarbons and most chemicals
- Meets EPA regulations for spill containment
- Grommets every 6' in skirt allows Berm to be secured In place
- Simple cleaning and storage allows for repeated use
- Patch Kit comes standard with every Snap-Up Berm
- Available in a variety of colors including Black, OD Green, Desert Tan and Blue
- Custom sizes are available upon request



Part #	Dimensions	Gallons
SB5512	5' X 5' X 12"	187 gal
SB8812	8' X 8' X 12"	473 gal
SB101012	10' X 10' X 12"	748 gal
SB123612	12' X 36' X 12"	3,231 gal
SB145412	14' X 54' X 12"	5,650 gal

*This data is provided for informational purposes only. GeoCHEM, Inc. makes no warranties as to the suitability or the fitness for a specific use or merchantability of products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check GeoCHEM, Inc. for current updates.*

Sales & Procurement Center - Phone No. (907) 562-5755 ~ Fax No. 206.219.3740  
 WA State Sales - Phone No. (206) 774.8777 ~ Toll Free: 1 (800) 490.5320  
 GeoCHEM Website: <http://www.geocheminc.com>  
 Contact Us: <http://www.geocheminc.com/contactus.php>

# SPEC SHEET – Snap Up Berm

## Gallons and dims by wall size

Width	Length	8"/ Gallons	8"/Outside Dims	12"/ Gallons	12"/Outside Dims
10'	10'	493	11'-4" X 11'-4"	748	12' X 12'
10'	20'	987	11'-4" X 21'-4"	1496	12' X 22'
12'	36'	2132	13'-4" X 37'-4"	3231	14' X 38'
14'	54'	3732	15'-4" X 55'-4"	8886	16' X 56'

Fabric: 30 oz. Hydrocarbon / chemical resistant  
 Standard Colors: Black, Tan, Green

Base Fabric Type	US	Metric
	Polyester	
Base Fabric Weight (nominal)	8 oz/yd <sup>2</sup>	270 g/m <sup>2</sup>
Thickness	36 mils min	0.91 mm
Weight	30.0+ <sub>-</sub> 2 oz/yd <sup>2</sup>	1020+ <sub>-</sub> 70 g/m <sup>2</sup>
Tear Strength, Tongue D751B	120/120 lb min	534/534 N min
Breaking Yield Strength ASTM D 751, Grab Tensile, Procedure	625/600 lb min	2780/2670 N min
Low Temperature ASTM D 2136,	Pass @ -40 F	Pass @ -40 C
Dimensional Stability ASTM D 1204, 212 F- 1 hr	2.5% max each direction	
Adhesion - Heat Sealed Seam ASTM D 751, Dielectric Weld	25 lb/2 in min	111 N/5 cm min
Bursting Strength ASTM D 751, Ball Tip	1000 lb min	4450 N
Hydrostatic Resistance ASTM D 751, Method A	800 psi min	540 N/sq cm min
Blocking Resistance ASTM D 751, 180 F/82 C	# 2 Rating max	
UV Resistance	8000 hrs	
Puncture Resistance ASTM D 4833	220 lb min	1110 N min

*This data is provided for informational purposes only. GeoCHEM, Inc. makes no warranties as to the suitability or the fitness for a specific use or merchantability of products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check GeoCHEM, Inc. for current updates.*