GEO SKRIM 2 & 10HUV

Four-Layer Reinforced Extrusion Laminate

Product Description

ÕÒU ÙSÜQ ® 2 B 10HUV consist of two sheets of highstrength virgin polyethylene film laminated together with a third layer of molten polyethylene. A heavy-duty scrim reinforcement placed between these plies greatly enhances tear-resistance and increases service life.

HIGH-STRENGTH
POLYETHYLENE FILM

MOLTEN POLYETHYLENE
BONDING LAYER

REINFORCED SCRIM

HIGH-STRENGTH
POLYETHYLENE FILM

ÕÒU ÙSÜQ 's heavy-duty diamond reinforcement responds to

tears immediately by surrounding and stopping the tear.

Product Use

ÕÒU ÙSÜQT [®] 2 is used for temporary applications that require a lightweight yet highly tear-resistant film such as building enclosures and abatement applications.

ÕÒU ÙSÜQ * 10HUV is used in applications that require good outdoor life and demand high puncture and tear strengths. The two outer layers of ÕÒU ÙSÜQ * 10HUV contain high concentrations of UV inhibitors and thermal stabilizers to assure added outdoor life up to approximately one year.

Size & Packaging

ÕÒU ÙSÜQ [®] 2 stock sizes are 6, 8, 10, 12, 16, 20, 24, 32 and 40 feet wide and 100 feet long.

ÕÒU ÙSÜQ * 10HUV is available in a variety of widths and lengths up to 100,000 square foot panels.

All panels are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time saving installation. Custom sizes are available.



Building Enclosure

Product	Part #
GEOKSKRIM 2	R5CC
GEOKSKRIM 10HLIV	R10CCU

APPLICATIONS

Construction Enclosures
Temporary Liners or Covers
Erosion Control
Shipping and Packaging
Temporary Erosion Control

Asbestos Abatements Fumigation Covers Temporary Walls Remediation Covers





2 & 10HUV



Four-Layer Reinforced Extrusion Laminate

		õòu ùsü a ÁGÁ		ÕÒU ÙSÜQ ÆF⊕WX		
PROPERTIES	TEST METHOD	Imperial	Metric	Imperial	Metric	
A PPEARANCE		Colorless		Colorless		
THICKNESS, NOMINAL		6 mil	0.15 mm	10 mil	0.25 mm	
WEIGHT		19 lbs/MSF 2.7 oz./yd ²	93 g/m ²	41 lbs/MSF 5.9 oz./yd ²	200 g/m ²	
Construction		Extrusion laminated with scrim reinforcement				
TENSILE STRENGTH bbf/in. (N/cm)	ASTM D7003	40 lbf	178 N	60 lbf	267 N	
ELONGATION AT BREAK	ASTM D7003	400 %	400 %	800 %	800 %	
GRAB TENSILE	ASTM D7004	60 lbf	267 N	85 lbf	378 N	
*TRAPEZOID TEAR	ASTM D4533	65 lbf	289 N	70 lbf	311 N	
Mullen Burst	ASTM D751	45 psi	310 kPa	90 psi	621 kPa	
MAXIMUM USE TEMPERATURE		180°F	82°C	180°F	82°C	
MINIMUM USE TEMPERATURE		-70°F	-57°C	-70°F	-57°C	
PERMEABILITY						
WVTR	ASTM E96 Procedure B	0.058 g/100in²/day	0.90 g/m²/day	0.017 g/100in²/day	0.27 g/m²/day	
PERM RATING	ASTM E96 Procedure B	0.13 Perms g/(ft²·hr·in·Hg)	0.86 Perms g/(24hr·m²·mm Hg)	0.039 Perms g/(ft²·hr·in·Hg)	0.026 Perms g/(24hr·m²·mm Hg)	

^{*}Tests are an average of diagonal directions.

GEOKSKRIM® 2 is a clear four layer reinforced extrusion laminate. The outer layers consist of a clear high-strength polyethylene film. GEOKSKRIM® 2 is reinforced with a minimum of a 1000 denier scrim laid in a diagonal pattern spaced 3/8" apart with an additional machine direction scrim every 9" across the width. The individual plies are laminated together with molten polyethylene.

GEOKSKRIM® 10HUV is a clear, four-layer reinforced extrusion laminate. The outer layers consist of a high strength polyethylene film with a high concentration of U.V. and thermal stabilizers. GEOKSKRIM® 10HUV is reinforced with a minimum of a 1000 denier scrim laid in a diagonal pattern spaced 3/8" apart with an additional machine direction scrim every 3" across the width. The individual plies are laminated together with molten polyethylene.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/ or conditions. GEOCHEM, INC. MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage.

GeoCHEM, Inc. - Phone: (907) 562-5755 ~ Fax: 206.219.3740 WA State Sales - Phone: (206) 774.8777 ~ Toll Free: 1 (800) 490.5320

http://www.geocheminc.com

