


Product Description

GEO♦SKRIM® 6BB, 6WB & 6WW are economical, reinforced films designed for applications requiring puncture resistance and high tear strengths. A heavy-duty scrim reinforcement, laminated between two layers of virgin high-strength polyethylene film, results in a material that resists punctures and immediately stops tears. The addition of carbon black and ultra violet inhibitors to GEO♦SKRIM® 6BB, 6WB and 6WW, respectively, increases outdoor longevity. GEO♦SKRIM® 6 is the first choice for applications requiring greater performance than common 6 and 10 mil plastic sheeting.



Product Use

GEO♦SKRIM® 6BB, 6WB & 6WW are used in short to mid-term applications requiring a light weight, tear-resistant, reinforced film. The white side of GEO♦SKRIM® 6WB and 6WW are excellent choices for covering applications that require minimal heat build up and condensation. GEO♦SKRIM® 6WW meets or exceeds ASTM E-1745, Class "C" standard as an underslab vapor retarder and is an excellent choice as an in-wall and roof vapor retarder as well.

Size & Packaging

GEO♦SKRIM® 6BB, 6WB & 6WW are available in a variety of widths and lengths. Panel sizes up to 100,000 square feet are available. All panels are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time-saving installation.



Construction Site Covers

Product

Part

GEO♦SKRIM 6BB.....	R6BB
GEO♦SKRIM 6WB.....	R6WBK
GEO♦SKRIM 6WW	R6WWK

APPLICATIONS

- | | |
|---------------------------|------------------------|
| Construction Site Covers | Insulation Membranes |
| Temporary Erosion Control | Building Enclosures |
| Lumber Covers | Concrete Curing Covers |
| Shipping Covers | Silage Covers |
| Pallet Covers | Temporary Walls |
| Remediation Covers | Fumigation Covers |
| Cargo Wraps | |



PROPERTIES	TEST METHOD	GEO♦SKRIM 6BB		GEO♦SKRIM 6WB		GEO♦SKRIM 6WW	
		IMPERIAL	METRIC	IMPERIAL	METRIC	IMPERIAL	METRIC
APPEARANCE		Black/Black		White/Black		White/White	
THICKNESS, NOMINAL		6 mil	0.15 mm	6 mil	0.15 mm	6 mil	0.15 mm
WEIGHT		24 lbs/MSF 3.5 oz/yd ²	117 g/m ²	27 lbs/MSF 3.9 oz/yd ²	132 g/m ²	28 lbs/MSF 4.0 oz/yd ²	137 g/m ²
CONSTRUCTION		Extrusion laminated with scrim reinforcement					
TENSILE STRENGTH lbf/in. (N/cm)	ASTM D7003	60 lbf	105 N	60 lbf	105 N	60 lbf	105 N
ELONGATION AT BREAK	ASTM D7003	450 %	450 %	450 %	450 %	450 %	450 %
GRAB TENSILE	ASTM D7004	75 lbf	333 N	75 lbf	333 N	75 lbf	333 N
*TRAPEZOID TEAR	ASTM D4533	50 lbf	222 N	50 lbf	222 N	50 lbf	222 N
MULLEN BURST	ASTM D751	60 psi	413 kPa	60 psi	413 kPa	60 psi	413 kPa
MAXIMUM USE TEMPERATURE		180°F	82°C	180°F	82°C	180°F	82°C
MINIMUM USE TEMPERATURE		-70°F	-57°C	-70°F	-57°C	-70°F	-57°C
WVTR	ASTM E96 Method A	0.03 g/100in ² /day	0.5 g/m ² /day	0.03 g/100in ² /day	0.5 g/m ² /day	0.03 g/100in ² /day	0.5 g/m ² /day
PERM RATING	ASTM E96 Method A	0.07 Perms g/(ft ² ·hr·in·Hg)	(0.05) Perms g/(24hr·m ² ·mm Hg)	0.07 Perms g/(ft ² ·hr·in·Hg)	(0.05) Perms g/(24hr·m ² ·mm Hg)	0.07 Perms g/(ft ² ·hr·in·Hg)	(0.05) Perms g/(24hr·m ² ·mm Hg)

*Tests are an average of diagonal directions.

GEO♦SKRIM® 6BB, 6WB & 6WW are four-layer reinforced extrusion laminates. The outer layers consist of a high-strength polyethylene. Carbon black in the 6BB and UV stabilizers in the 6WW increase longevity.

GEO♦SKRIM® 6BB, 6WB & 6WW are reinforced with a minimum of 1000 denier scrim laid in a diagonal pattern spaced 3/8" apart.

GEO♦SKRIM® 6WW meets or exceeds ASTM E-84 standard, Class "A" for surface burning characteristics of building materials and also ASTM E-1745, Class "C" standard for water vapor retarders used in contact with soil or granular fill under concrete slabs.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. GEOCHEM, INC. MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage.