

PROPERTIES	TEST METHOD	GEO SAFE	
		Imperial	Metric
CONSTRUCTION		Multi-layer Barrier Film	
APPEARANCE		Translucent	
THICKNESS, NOMINAL	ASTM D 5199	1 mil	0.03 mm
WEIGHT / AREA	ASTM 4321	5 lbs/MSF	24 g/m ²
*MASS TRANSFER COEFFICIENT		0.0001 mol/(s•m ²)/(mol/m ³)	0.0001 mol/(s•m ²)/(mol/m ³)
IMPACT RESISTANCE	ASTM D 1709 (A)	115 grams	115 grams
TENSILE STRENGTH @ BREAK	ASTM D 882	5 lbf/in MD 5 lbf/in TD	8.7 N/cm MD 8.7 N/cm TD
ELONGATION @ BREAK	ASTM D 882	637 % MD 707 % TD	637 % MD 707 % TD
PUNCTURE RESISTANCE	ASTM D 4833	4.3 lbf	19 N
MAXIMUM USE TEMPERATURE		180° F	82° C
MINIMUM USE TEMPERATURE		-70° F	-57° C

* Test results listed are based on the following information: Overview of Recent Fumigant Emissions Research, Charles Smith, Health Effects Division, Office of Pesticide Programs, U.S. EPA, 2010 MBAO Conference.

Geo Safe™ is a seven-layer co-extruded barrier films made from very flexible lineal low density polyethylene and an inner core of gas impermeable EVOH. High strength LLDPE provides exceptional tear and impact strengths to allow for ease of installation and long term performance. Utilizing **Geo Safe™** (TIF) can maximize production acres significantly impacting your overall bottom line while reducing fumigant rates up to 50% without loss of efficacy or yield.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. GEOCHEM, INC. MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage.