

GEO 8.0-205NW





GeoCHEM

INCORPORATED

Nonwoven Geotextile

NTPEP APPROVED - GTX-2013-01-030. GEO 8.0-205NW is a nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. GEO 8.0-205NW resists ultraviolet and biological deterioration, rotting, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. GEO 8.0-205NW will satisfy the requirements as outlined in AASHTO M-288-06 for Class 1 applications and meets the following M.A.R.V. values except where noted:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight - Typical	ASTM D-5261	8.0 oz/sy	271 g/sm
Tensile Strength	ASTM D-4632	205 lbs	912 N
Elongation @ Break	ASTM D-4632	50%	50%
Mullen Burst*	ASTM D-3786*	350 psi	2,413 kPa
Puncture Strength*	ASTM D-4833*	130 lbs	579 N
CBR Puncture	ASTM D-6241	535 lbs	2,381 N
Trapezoidal Tear	ASTM D-4533	85 lbs	378 N
Apparent Opening Size	ASTM D-4751	80 US Sieve	0.180 mm
Permittivity	ASTM D-4491	1.35 Sec-1	1.35 Sec-1
Water Flow Rate	ASTM D-4491	90 g/min/sf	3,657 l/m in/sm
UV Resistance @ 500 Hours	ASTM D-4355	70%	70%

ROLL SIZE	ROLL DIAMETER	AREA	WEIGHT
12.5' x 360'	16.0 in	500 sys	270 lbs
15' x 300'	16.0 in	500 sys	270 lbs

* Historical averages (current values not available): Mullen Burst Strength ASTM D3786 is no longer recognized by ASTM D-35 on Geosynthetics as an acceptable test method. Puncture Strength ASTM D4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241.

This information is provided for reference only and is not intended as a warranty or guarantee. GeoCHEM, Inc. assumes no liability in connection with the use of this information (1/2013).

GeoCHEM, Inc. - Phone: (907) 562.5755 ~ Fax: 206.219.3740
WA State Sales - Phone: (206) 774.8777 ~ Toll Free: 1 (800) 490.5320
<http://www.geocheminc.com>