


GEO 8.0-225NW

Nonwoven Geotextile



GeoCHEM
INCORPORATED

GEO 8.0-225NW is an 8 OZ MARV WEIGHT nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. GEO 8.0-225NW is resistant to ultraviolet deterioration, rotting, biological degradation, naturally encountered bases and acids. Polypropylene is stable within a pH range of 2 to 13. GEO 8.0-225NW meets the following M.A.R.V. values:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight	ASTM D-5261	8 oz/sy	271 g/sm
Tensile Strength	ASTM D-4632	225 lbs	1,000 N
Elongation @ Break	ASTM D-4632	50%	50%
Thickness	ASTM D-5199	100 mils (at time of manufacture)	2.5 mm (at time of manufacture)
CBR Puncture	ASTM D-6241	600 lbs	2,900 N
Trapezoidal Tear	ASTM D-4533	90 lbs	400 N
Apparent Opening Size	ASTM D-4751	80 US Sieve	0.180 mm
Permittivity	ASTM D-4491	1.26 Sec-1	1.26 Sec-1
Permeability	ASTM D-4491	0.3 cm/sec	0.3 cm/sec
Water Flow Rate	ASTM D-4491	100 g/min/sf	4,074 l/min/sm
UV Resistance @ 500 Hours	ASTM D-4355	70%	70%

ROLL SIZE	AREA	WEIGHT
15' x 300'	500 sqy	265 lbs

This information is provided for reference only and is not intended as a warranty or guarantee. GeoCHEM, Inc. assumes no liability in connection with the use of this information (1/2013).

GeoCHEM, Inc. - Phone: (907) 562.5755 ~ Fax: 206.219.3740
 WA State Sales - Phone: (206) 774.8777 ~ Toll Free: 1 (800) 490.5320
<http://www.geocheminc.com>