



PRODUCT INFORMATION • SPECIFICATION GUIDE HDPE ALLOY - 10.5 Mil Cross Laminated

PHYSICAL PROPERTIES AND TYPICAL VALUES	PROPERTY	ASTM TEST METHOD	U.S. VALUE	METRIC VALUE
	Weight	D-2103	32 LB/1000 FT ²	15.6 KG/100 M ²
	Thickness	D-2103	10.5 MIL	.27 MM
	1" Load @ Yield	D-882	16 LBF	71 N
	1" Load @ Break	D-882	35 LBF	156 N
			3300 PSI	24.1 MPA
	1" Elongation @ Break	D-882	575 %	575 %
	Tongue Tear	D-2261	10.5 LBF	47 N
	Trapezoidal Tear	D-4533	18 LBF	80 N
	PPT Resistance	D-2582	32 LBF	142 N
	Dart Impact Strength	D-1709	2 LBS	.91 KG
	Cold Impact Strength	D-1790	-40°F	-40°C
Permeability	E-96	.019 Grain/Hr•Ft ² •in.Hg	.019 Grain/Hr•Ft ² •in.Hg	

Sales & Procurement Center - Phone No. (907) 562-5755 ~ Fax No. 206.219.3740

WA State Sales - Phone No. (206) 774.8777 ~ Toll Free: 1 (800) 490.5320

GeoCHEM Website: <http://www.geocheminc.com> Contact Us: <http://www.geocheminc.com/contactus.htm>

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.