



PRODUCT INFORMATION • SPECIFICATION GUIDE HDPE ALLOY - 20 Mil Cross Laminated

PHYSICAL PROPERTIES AND TYPICAL VALUES	PROPERTY	ASTM TEST METHOD	U.S. VALUE	METRIC VALUE
	Weight	D-751	81 LB/1000 FT ²	40 KG/100 M ²
	Thickness	D-5199	20 MIL	.508 MM
	Load @ Yield	D-882	37 LBF	165 N
	Load @ Break	D-882	75 LBF	334 N
			3900 PSI	26.8 MPA
	Elongation @ Break	D-882	550 %	550 %
	Tongue Tear	D-2261	28 LBF	125 N
	Trapezoidal Tear	D-4533	44 LBF	196 N
	PPT Resistance	D-2582	50 LBF	222 N
	Dart Impact Strength	D-1709	3.5 LBS	1.6 KG
Puncture Strength	D-4833	45 LBS	200 MPA	
Permeability	E-96	.0143 Grain/Hr•Ft ² •In.Hg		

- Cross-laminated polyethylene resists punctures and tears.
- UV stabilized to withstand prolonged exposure to sunlight.
- Is not prone to environmental stress-cracking (ESC) so it can endure repeated thermal expansion & contraction cycles.

Sales & Procurement Center - Phone No. (907) 562-5755 ~ Fax No. 206.219.3740

WA State Sales - Phone No. (206) 774.8777 ~ Toll Free: 1 (800) 490.5320

GeoCHEM Website: <http://www.geocheminc.com> Contact Us: <http://www.geocheminc.com/contactus.htm>

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.